








# STONE PORT

## METALS

### COLOURED BODY PORCELAIN STONEWARE

SPECIFICATION REFERENCE E.N. 14411 . APPENDIX G. GROUP BIA. GL		TEST METHOD	REFERENCE VALUE	DECLARED VALUE
	Dynamic coefficient of friction	ANSI-137-1	-	-
	Dynamic coefficient of friction		-	≥ 0.36* SEMPOLISHED
	Chemical resistance	ASTM-650	-	NOT AFFECTED
	Surface abrasion	ASTM-C1027	-	IV SEMPOLISHED
	Surface abrasion		-	IV MATTE
	Stain Resistance	ASTM-C1378	-	NOT AFFECTED
	Water absorption	ASTM-C373	-	≤ 0.5%
	Breaking strength	ASTM-C648	-	> 400 (9 mm), ≥ 300 (8 mm)
	Scratch hardness	MOHS	-	> 7